

IN THE SPECIFICATION

Please replace paragraph [0092] beginning at page 30 with the following rewritten paragraph:

[0092]

<Comparative example 1>

~~Example 8~~ Comparative example 1 shows an example using polymer particles (A1) having the core/shell structure as the polymer particles (A) of liquid composition (LA), diisononyl phthalate as the dispersion medium (B) and di-2-ethylhexyl phthalate as liquid composition (LB). Gelation property was insufficient because no gelation was observed within 60 minutes after these two liquids were mixed.

Please replace paragraph [0093] beginning at page 30 with the following rewritten paragraph:

[0093]

<Comparative example 2>

~~Example 8~~ Comparative example 2 shows an example using polymer particles (A2) having the core/shell structure as the polymer particles (A) of liquid composition (LA), diisononyl phthalate as the dispersion medium (B), an acrylic monomer having a radical-polymerizable double bond which is disclosed in Japanese Patent Laid-Open No. 2002-30194 as liquid composition (LB) and benzoyl peroxide as a radical polymerization initiator. Gelation property was insufficient because no gelation was observed within 60 minutes after these two liquids were mixed.